

**ENAMEL**  **HRi Flow<sup>HF</sup>**  
*plus*



COMPLETE KIT

**CHR2F**

ENAMEL PLUS HRI FLOW  
 UD0, UD0,5, UD1 (A1), UD2 (A2) 9 x 2 g  
 UD3 (A3), UD3,5 (A3,5), UD4, UD5, UD6  
 Plexiglass holder



MINI KIT

**CHR5F**

ENAMEL PLUS HRI FLOW  
 UD1 (A1), UD2 (A2) 5 x 2 g  
 UD3 (A3), UD3,5 (A3,5), UD4

**ENAMEL PLUS**  
**HRI FLOW**



Micerium S.p.A.  
 Via G. Marconi, 83-16036 Avegno (GE) Italy  
 Tel. +39 0185 7887 880 • Fax +39 0185 7887 970  
 hfo@micerium.it • www.micerium.com





File: Enamel plus Hri Flow ING v1.0\_10-2013



**NO BUBBLES**

**Higher Elasticity**



ANALYSIS UNDER MAGNIFICATION

PHYSICAL CHARACTERISTICS

|               | FILLER% | VICKERS HARDNESS MPa | YOUNG MODULUS MPa | FLEXURAL STRENGTH MPa | COMPRESSIVE STRENGTH MPa | RADIOPACITY |
|---------------|---------|----------------------|-------------------|-----------------------|--------------------------|-------------|
| HRi "Flow HF" | 77      | 770                  | 13485             | 148                   | 394                      | 210% AI     |
| Standard Flow | 55      | 350                  | 6000              | 120                   | 350                      | 30% AI      |

- Highly Filled
- Highly Fluorescent
- Higher Viscosity
- Higher Elasticity
- Higher Radiopacity
- High Physical Properties
- No bubbles

**Highly Fluorescent**



Material to be used as cavity liner in posteriors for direct and indirect restorations and in anteriors for class V build up.